

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C09D 127/06, 163/00, C09K 3/10	A1	(11) International Publication Number: WO 98/37159 (43) International Publication Date: 27 August 1998 (27.08.98)
(21) International Application Number: PCT/EP98/00943 (22) International Filing Date: 19 February 1998 (19.02.98) (30) Priority Data: 197 06 810.3 21 February 1997 (21.02.97) DE (71) Applicant (for all designated States except US): PPG INDUSTRIES, INC. [US/US]; One PPG Place, Pittsburgh, PA 15272 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): GROEN IN'T WOUDE, Wilhelmina, Andrea, Maria [NL/NL]; Beusichemstraat 32, NL-4001 TL Tiel (NL). SCHOOTS, Johannes [NL/NL]; Helbouwlaan 10, NL-4006 XJ Tiel (NL). (74) Agent: STERNAGEL & FLEISCHER; Braunsberger Feld 29, D-51429 Bergisch Gladbach (DE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: INTERIOR COATING MATERIAL FOR CONTAINER CLOSURES (57) Abstract The invention teaches an interior coating material for container closures, having the following components: a) a polymer from the group consisting of epoxy resins based on bisphenol A diglycidyl ether or bisphenol F diglycidyl ether, epoxidized novolaks, phenol-formaldehyde condensates, acrylate resins, polyester resins and melamine resins, or a mixture of such polymers, b) a halogenated polymer from the group consisting of the polyvinyl chlorides (PVC), or a mixture of such halogenated polymers, c) a substance from the group consisting of TiO ₂ , SiO ₂ , Fe ₂ O ₃ and BaSO ₄ , or a mixture of such substances, and d) a customary solvent or a mixture of such solvents. The amounts of components a), b) and c) employed are chosen subject to the proviso that the ready-to-apply interior coating material has an overall solids content of more than 40 % by weight. The proportion of the employed components b) and c) to the employed component a) is greater than 0.5 : 1. The proportion of component b) to component c) is within the range from 0.5 : 1 to 1 : 1.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KR	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KZ	Kazakhstan	PT	Portugal		
CN	China	LC	Saint Lucia	RO	Romania		
CU	Cuba	LI	Liechtenstein	RU	Russian Federation		
CZ	Czech Republic	LK	Sri Lanka	SD	Sudan		
DE	Germany	LR	Liberia	SE	Sweden		
DK	Denmark			SG	Singapore		
EE	Estonia						

Interior coating material for container closures

The invention relates to an interior coating material for container closures, based on resin, to a process for preparing such an interior coating material, and to uses of such an interior coating material for producing coated container closures which may or may not comprise sealing materials. - Container closures is the term for closures which are screwed on, placed on, inserted in or formed onto container apertures. Examples are screw caps or crown corks for food containers which hold at least partly liquid foods, liquid preserving agents or beverages. Container closures for this end use are subject to particular requirements. On the one hand, the sealing provided to the contents must be liquid-tight and, in the case for example, of contents which include or give off gases, must be gastight as well. On the other hand, the base material of the container closures must be protected against corrosive attack by the contents. An interior coating material of the invention can in principle, however, be used for non-food container closures as well. Base materials employed in principle are both polymeric materials and metallic materials, examples being sheet iron (in general, coated electrolytically with tin), sheet aluminum or tinfoil, the metallic

- 2 -

materials in particular having acquired wider currency. Gastight sealing is generally achieved by means of a seal which is manufactured, for example, from an elastomer and which when the container is in the closed state is arranged in the region of the sealing faces of the container aperture and of the container closure. Seals of this kind are either prefabricated from an appropriate sealing material and inserted into the container closure or applied, as it were, as a coating on the inside of the container closure. In addition, however, it is generally necessary, especially when using metallic materials as the base materials for a container closure, to protect the entire inner face of the container closure against corrosive attack by the contents through the application of an interior coating material. This interior coating material is then arranged between the sealing material and the base material of the container closure. The coating itself can be of single-coat or else multi-coat design, for example with a primer coat and a topcoat. In the latter case, the expression interior coating material designates a coating material for producing the topcoat. Consequently, such an interior coating material must on the one hand be suitable for food contact (in accordance with statutory regulations) and on the other hand must be chemically inert (to the contents). Also of particular importance is the fact

- 3 -

that the interior coating material must show good adhesion both to the base material (or to the primer coat) and to the sealing material. Finally, the interior coating material is required to have physical properties which ensure no processing problems in the roller coating technology that is customary in the manufacture of container closures. In this technology, a tin-plated iron sheet, for example, is first of all provided with a coating of the interior coating material by means of roller coating. The container closures are then obtained from the coated sheet by means of cutting and/or shaping tools and are provided with the sealing material. In principle, however, it is possible to apply the sealing material to the coated sheet before cutting or shaping.

Interior coating materials of the type specified at the outset are known, for example, from reference US-3,183,144. These known interior coating materials are formed essentially from synthetic resins. Examples indicated of synthetic resins are phenol-formaldehyde condensates, oleoresins and epoxy resins. A common feature of all these known interior coating materials is that their solids content is relatively low, namely below 40% by weight. It would in contrast be desirable to be able to operate with a higher solids content, since then less solvent would be required. Less solvent would entail not only lower solvent costs

- 4 -

but also, in particular, a lower level of solvent emission on application. Moreover, according to experience to date, the solids content cannot be raised simply by adding, say, TiO_2 , since this will adversely affect the physical and/or chemical properties of the coating material. Up until now, therefore, a level of 40% by weight for the overall solids content has been regarded as an upper limit if processability, and physical and/or chemical properties, are still to satisfy these requirements.

Against this background, the technical problem on which the invention is based is to specify an interior coating material whose solids content is markedly increased but which nevertheless satisfies all the requirements in respect of the physical and/or chemical properties and processability, the adhesion between interior coating material and base material (or primer coat) and between interior coating material and sealant coat, and the resistance to aggressive contents.

In order to solve this technical problem the invention teaches an interior coating material for container closures, having the following components:

a) a polymer from the group consisting of epoxy resins based on bisphenol A diglycidyl ether or bisphenol F diglycidyl ether, epoxidized novolaks, phenol-formaldehyde condensates, acrylate resins, polyester

- 5 -

resins and melamine resins, or a mixture of such polymers, b) a halogenated polymer from the group consisting of polyvinyl chlorides (PVC), or a mixture of such halogenated polymers, c) a substance from the group consisting of TiO_2 , SiO_2 , Fe_xO_y and BaSO_4 , or a mixture of such substances, and d) a customary solvent or a mixture of such solvents, the amounts of components a), b) and c) employed being chosen subject to the proviso that the ready-to-apply interior coating material has an overall solids content of more than 40% by weight, with the proportion (based on the solids) of the employed component b) and c) to the employed component a) being greater than 0.5 : 1 and with the proportion (based on the solids) of component b) to component c) being within the range from 0.5 : 1 to 10 : 1.

- Epoxidized novolaks are epoxidized polycondensates of formaldehyde and phenols, which are prepared under acid catalysis. Novolaks contain no methylol groups and belong to the group of the phenolic resins. It is also possible in principle, however, to employ phenolic resins which do not belong to the novolaks group. Acrylate resins are thermoplastic or heat-curable resins which are obtained by homo- or copolymerization of (meth)acrylic esters. Functional groups, such as hydroxyl or carboxyl groups, can be introduced by way of comonomers. Polyester resins are polycondensation products of carboxylic acids having a

- 6 -

functionality of two or more with alcohols. Melamine resins are polycondensates of melamine with carbonyl compounds, especially with formaldehyde, possibly modified with urea and/or phenol. The group of the
5 polyvinyl chlorides also includes those halogenated vinyl chloride polymers which are modified with, for example, (meth)acrylates, vinyl acetate, maleic acid, vinylidene chloride or acrylonitrile. Examples of customary solvents are butanol, butylglycol, diacetone
10 alcohol (4-hydroxy-4-methyl-2-pentanone), hydrocarbons, and solvents obtainable commercially under the designations Imsol R or Solvesso 150. Imsol R is a mixture of dimethyl esters of adipic, glutaric and succinic acids.

15 The following substances are particularly preferred as components a) and c). A particularly suitable component a) is a preferably thermoplastic acrylate resin. Such resins preferably also comprise high molecular mass, noncrosslinking polyacrylate
20 resins which as monomers preferably include acrylic acid, acrylonitrile, acrylamide and also modifications and mixtures thereof. The preferred component c) is essentially TiO_2 . For coloring or for adjusting the gloss it is possible, for example, to add small amounts
25 of iron oxide pigments (Fe_xO_y) and/or SiO_2 .

The invention is based on the finding that the overall solids content of an interior coating material

- 7 -

can surprisingly be raised without impairing the properties, especially the processability, if the ratio of the amounts of halogenated polymer and of substance from the group consisting of TiO_2 , SiO_2 , Fe_xO_y and BaSO_4 are specially attuned to one another. A marked increase only in the proportion of, say, TiO_2 would lead not only to poorer processability but also to a marked impairment of the chemical resistance of a coating produced from such an interior coating material. An interior coating material of the invention, on the other hand, has the advantage that - with retention of all the necessary properties, i.e. adhesion to the substrate, adhesion to the sealant, chemical resistance of a resulting coating to contents, the possibility of producing virtually pore-free coatings (corrosion protection for the substrate) and good processability in the customary technology for producing container closures - a particularly high overall solids content and, consequently, a considerable cost reduction in terms of the solvent, and a considerable reduction in the solvent emission on application, have been achieved. It has also been found, in addition to the good properties in the actual coating process, that, surprisingly, cutting tools which are employed in the course of the subsequent processing of the coated sheets are not worn down or stressed to any greater extent. The reason why this is surprising is that, from

- 8 -

simple considerations based on the increase in the proportion of "hard" components (e.g. TiO_2 and PVC), greater cutting-tool wear would have been expected.

In a preferred embodiment of the invention an additional component present in the interior coating material is a substance from the group of the plasticizers, or a mixture of such substances. With regard to suitable plasticizers reference is made, for example, to DIN 7723, Dec. 1987. Particularly preferred plasticizers are those from the group consisting of epoxidized oils, soya oil, linseed oil, low molecular mass polyesters and natural-product plasticizers.

Advantageously, the proportion of the employed components b) and c) to the employed component a) is greater than 1 : 1. The proportion of the halogenated polymer or of the mixture of such halogenated polymers to the substance that is employed from the group consisting of TiO_2 , SiO_2 , Fe_xO_y and BaSO_4 , or to the mixture of such substances, is preferably within the range from 1 : 1 to 4 : 1 and, with particular preference, within the range from 1 : 1 to 2 : 1. The amounts of components a), b) and c) that are employed are preferably chosen subject to the proviso that the ready-to-apply interior coating material has an overall solids content of more than 45% by weight, most preferably more than 50% by weight.

- 9 -

The invention also teaches a process for preparing an interior coating material as claimed in any of claims 1 to 5, in which a first portion of component a) is mixed with the total amount of component c) and with a first portion of component d) to give a pigment paste, and in which component b) is mixed with a second portion of component a) and with a second portion of component d) to give a PVC paste, the pigment paste and the PVC paste being mixed with one another, with or without the addition of a mixture of the remainder of component a) and of the remainder of component d), and in which the resulting mixture is stirred homogeneously. Furthermore, the invention teaches the use of an interior coating material of the invention for producing a container closure, the inside of the container closure being provided with a coating of the interior coating material, and the use of an interior coating material of the invention for producing container closures, in which the interior coating material is applied by means of roller coating technology to at least one side of a sheet of raw material, in particular a metal sheet, and where, after the interior coating material has cured fully to form a coating, the container closures are separated and shaped from the raw material sheet by means of punching, cutting and/or pressing tools and where a sealant coat is applied to the coating before or after

- 10 -

the cutting or shaping of the container closures.
Examples of suitable metal sheet materials are:
tinplate, aluminum, chromated steel and tin-free steel.
Specifically, the interior coating material can be
5 applied directly to the raw material sheet, although it
is also possible to interpose a primer between interior
coating material and raw material sheet.

The invention is elucidated further below on
the basis of examples which represent merely
10 embodiments of the invention.

Materials used jointly in the examples

The acrylate resin employed was a noncross-
linking thermoplastic acrylate resin of high molecular
mass. The primer employed - where appropriate - was a
15 material customary in food container technology, which
is essentially an epoxy-phenol coating material with a
relatively high content of phenol-formaldehyde resin.
The sealing material employed was a material customary
in food container technology. Customary materials are
20 based, for example, on polymers (plasticizers,
phthalates), silicones, epoxy esters or polyurethanes.

Example 1

A PVC paste was prepared from the following
25 components: 22.03 parts by weight of the acrylate
resin, 24.93 parts by weight of a halogenated polymer
with the trade name Geon 178, 9.22 parts by weight of a

- 11 -

solvent with the trade name Solvesso 150, 10.20 parts by weight of a solvent with the trade name Imsol R and 6.12 parts by weight of the solvent diacetone alcohol. A pigment paste was prepared from the following components: 18.31 parts by weight of TiO₂ (trade name TiPure R900), 1.76 parts by weight of a bisphenol A-formaldehyde condensate (butylated) with the trade name Uravar FB 210, 4.72 parts by weight of an epoxidized novolak with the trade name DEN 431 BS and 8.08 parts by weight of the solvent with the trade name Solvesso 150. 68.60 parts by weight of the abovementioned PVC paste were combined with 32.87 parts by weight of the abovementioned pigment paste, with the addition of 0.63 part by weight of an amorphous wax ester fraction of partially hydrogenated lanolin, having the trade name Lanocerin, 0.65 part by weight of phosphoric acid (85% strength in water, mixed beforehand in isopropanol before addition to the coating material) and 1.85 parts by weight of the solvent with the trade name Solvesso 150. The solids content of the interior coating material was 50.3% (9000 kg batch with a processing viscosity of 96 s in accordance with DIN 4 (cup) at 25°C). The ratio of the amount of component b) to the amount of component c) was 2.84 : 1. The ratio of the amounts of components b) and c) to the amount of component a) was 1.34 : 1.

- 12 -

An interior coating material obtained in this way was applied to a primed, tin-plated iron sheet and stoved at 190°C for 10 minutes. The resulting coating showed very good properties in terms of gloss, leveling
5 behavior, flexibility, MEK resistance and corrosion resistance, in the case of the coating properties both before and after sterilization at 129°C for 60 minutes.

Example 2

10 In a manner similar to that of Example 1, an interior coating material was prepared from the following components: 30.34 parts by weight of the acrylate resin from Example 1, 15.14 parts by weight of TiO₂ with the trade name TiPure R900, 19.49 parts by
15 weight of the halogenated polymer with the trade name Geon 178, 2.69 parts by weight of the bisphenol A-formaldehyde condensate (butylated) with the trade name Uravar FB 210, 6.86 parts by weight of a novolak with the trade name DEN 431 BS, 6.40 parts by weight of
20 butylglycol, 3.73 parts by weight of the solvent with the trade name Imsol R, 4.62 parts by weight of diacetone alcohol, 1.95 parts by weight of butanol, 0.85 part by weight of an amorphous wax ester fraction of partially hydrogenated lanolin with the trade name
25 Lanocerin, 0.50 part by weight of isopropanol, 0.05 part by weight of phosphoric acid (concentration as in Example 1), 2.47 parts by weight of an epoxidized

- 13 -

soya oil with the trade name Edenol D81, 4.71 parts by weight of the solvent with the trade name Solvesso 150 and 0.20 part by weight of an additive with the trade name Syloid 244.

5 The solids content of the resulting interior coating material was about 51%. The ratio of the amount of component b) to the amount of component c) was 1.29 : 1. The ratio of the amounts of components b) and c) to the amount of component a) was 0.82 : 1. The
10 viscosity in accordance with DIN 4, 25°C, was 75". On storage below room temperature for 8 weeks there was only a slight rise in viscosity. Even after storage for 8 weeks in a warm room (40°C) there was no gelling, thus demonstrating the outstanding long-term stability
15 of the interior coating material. A coating produced with an interior coating material as per this example on a tin-plated iron sheet with a primer showed good leveling (virtually no stripes when processed by the roller application process), a gloss of about 70
20 (customary 60° measurement), excellent adhesion to the sealing material (both before and after normal sterilization and high-temperature sterilization at 129°C in water for 60 minutes; crosshatch method), very good flexibility in the course of the further
25 processing of the coated sheets by shaping, and an MEK resistance of 9 (double strokes with a cotton pad saturated with MEK).

- 14 -

Example 3

In a manner similar to that of Example 1, an interior coating material was prepared from the following components: 26.20 parts by weight of the acrylate resin from Example 1, 13.08 parts by weight of TiO₂ with the trade name TiPure R900, 25.23 parts by weight of the halogenated polymer with the trade name Geon 178, 2.31 parts by weight of the bisphenol A-formaldehyde condensate (butylated) with the trade name Uravar FB 210, 3.35 parts by weight of a bisphenol A diglycidyl ether with the trade name Epikote 880, 3.79 parts by weight of butylglycol, 15.14 parts by weight of diacetone alcohol, 5.90 parts by weight of butanol, 0.74 part by weight of an amorphous wax ester fraction of partially hydrogenated lanolin with the trade name Lanocerin, 0.43 part by weight of isopropanol, 0.05 part by weight of phosphoric acid (concentration as in Example 1 and 3.78 parts by weight of the solvent with the trade name Solvesso 150.

The solids content of the resulting interior coating material was about 52%. The ratio of the amount of component b) to the amount of component c) was 1.93 : 1. The ratio of the amounts of components b) and c) to the amount of component a) was 1.34 : 1. The viscosity in accordance with DIN 4, 25°C, was 64". On storage below room temperature for 8 weeks there was

- 15 -

only a slight rise in viscosity. Even after storage for 8 weeks in a warm room (40°C) the viscosity rose to only 78". A coating produced with an interior coating material as per this example on a tin-plated iron sheet
5 with a primer showed good leveling a gloss of better than 70, excellent adhesion to the sealing material (both before and after normal sterilization and high-temperature sterilization at 129°C in water for 60 minutes), a flexibility much better even than
10 Example 2 in the course of the further processing of the coated sheets by shaping, and an MEK resistance of 9 (double strokes with a cotton pad saturated with MEK).

- 16 -

Claims

1) An interior coating material for container closures, having the following components:

5

a) a polymer from the group consisting of epoxy resins based on bisphenol A diglycidyl ether or bisphenol F diglycidyl ether, epoxidized novolaks, phenol-formaldehyde condensates, acrylate resins, polyester resins and melamine resins, or a mixture of such polymers,

10

b) a halogenated polymer from the group consisting of polyvinyl chlorides (PVC), or a mixture of such halogenated polymers,

15

c) a substance from the group consisting of TiO_2 , SiO_2 , Fe_xO_y and BaSO_4 , or a mixture of such substances, and

20

d) a customary solvent or a mixture of such solvents,

the amounts of components a), b) and c) employed being chosen subject to the proviso that the ready-to-apply interior coating material has an overall solids content of more than 40% by weight,

25

- 17 -

with the proportion (based on the solids) of the employed components b) and c) to the employed component a) being greater than 0.5 : 1 and

5

with the proportion (based on the solids) of component b) to component c) being within the range from 0.5 : 1 to 10 : 1.

2) The interior coating material as claimed in claim 1, comprising as additional component a substance from the group of the plasticizers, or a mixture of such substances.

3) The interior coating material as claimed in either of claims 1 and 2, where the proportion of the employed components b) and c) to the employed component a) is greater than 1:1.

4) The interior coating material as claimed in any of claims 1 to 3, where the proportion of component b) to component c) is within the range from 1:1 to 4:1.

5) The interior coating material as claimed in any of claims 1 to 4, where the amounts of components a), b) and c) that are employed are chosen subject to the proviso that the ready-to-apply interior coating material has an overall solids content of more than 45% by weight.

6) A process for preparing an interior coating material as claimed in any of claims 1 to 5, in which a

- 18 -

first portion of component a) is mixed with the total amount of component c) and with a first portion of component d) to give a pigment paste, and in which component b) is mixed with a second portion of component a) and with a second portion of component d) to give a PVC paste, the pigment paste and the PVC paste being mixed with one another, with or without the addition of a mixture of the remainder of component a) and of the remainder of component d), and in which the resulting mixture is stirred homogeneously.

7) The use of an interior coating material as claimed in any of claims 1 to 5 for producing a coated container closure, the inside of the container closure being provided with a coating of the interior coating material.

8) The use of an interior coating material as claimed in any of claims 1 to 5 for producing coated container closures, in which the interior coating material is applied by means of roller coating technology to at least one side of a sheet of raw material, in particular a metal sheet, and where, after the interior coating material has cured fully to form a coating, the container closures are separated and shaped from the raw material sheet by means of punching, cutting and/or pressing tools and where a sealant coat is applied to the coating before or after the cutting and shaping of the container closures.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/00943

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C09D127/06 C09D163/00 C09K3/10		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C09D C09K		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 514 433 A (COLE) 7 May 1996 see column 3, line 44 - column 9, line 65; claims 1-12; examples	1-5,7
X	EP 0 346 173 A (OWENS-ILLINOIS CLOSURE) 13 December 1989 see column 2, line 36 - column 3, line 55; claims 1-3; examples	1
A	FR 2 155 951 A (TH. GOLDSCHMIDT) 25 May 1973 see page 2, line 27 - page 3, line 2; claims 1-3; example 1	1
A	DE 20 29 629 A (HERMANN WIEDERHOLD) 23 December 1971 see page 2, line 30 - page 7, line 4; claims; example 1	1
-/-		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search 18 June 1998		Date of mailing of the international search report 26/06/1998
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo rd, Fax: (+31-70) 340-3016		Authorized officer Bourgonje, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/00943

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0 254 755 A (ICI LACKE FARBEN) 3 February 1988 see page 3, line 8 - page 5, line 22; claim 1; examples</p> <p>-----</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/00943

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5514433 A	07-05-1996	NONE	
EP 346173 A	13-12-1989	US 4949859 A	21-08-1990
		AU 602631 B	18-10-1990
		AU 3506289 A	05-04-1990
		CA 1339497 A	14-10-1997
		JP 2032145 A	01-02-1990
		US 5137164 A	11-08-1992
		US 5229428 A	20-07-1993
FR 2155951 A	25-05-1973	DE 2149460 A	12-04-1973
DE 2029629 A	23-12-1971	FR 2148392 A	23-03-1973
		NL 7105792 A	20-12-1971
EP 254755 A	03-02-1988	AU 610073 B	16-05-1991
		AU 7609587 A	04-02-1988